Printec® 250gsm Satin Resin Coated WP Photo Paper

PR WP 250 RC-S

Technical Information Sheet

Ink Compatibility: Aqueous Dye & Pigment

Physical Properties:

Property		Average Values	Test Method
Substrate		paper	
Finish		Satin	
Thickness	Base	/	ISO 534
	Liner	/	
	Total	270	
Basic Weight	Base	220	ISO 536
	Liner	/	
	Total	260±5	
Whiteness (CIE)		93	ISO 11476
Opacity without liner		96,80%	ISO 2470
Gloss (60°)		27,5	ASTM D-523
Surface Roughness（Ra）(front side)		0,43	
Paper Color	L*	90,87	
	a*	0,17	
	b*	-6,56	

Image Properties:

Property		Average Values	Test Method
Printer		HP 6100	
Color Density	C	2,39	
	M	1,90	
	Y	1,70	
	K	2,34	
8 color gamut volume		1863	
Dry Time		1.5min	26°C & 42% R.H.
Waterfastness		not waterproof	

Printec®

Operating Conditions: A conditioned pressroom, ± 23°C and ±50 % R.H. (Recommended).

Attention:

Data above are updated results and conclusions of test by Printec® and is subject to change without prior notice.

After printing the ink must be thoroughly dry in order to avoid any affect on the later combination with the laminate.

Printec® is not responsible for all the performance of this material for a given application, the users of materials should perform their own testing to determine the suitability of the material for the intended use.

Printec®